

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

10/512074

(19) World Intellectual Property Organization
International Bureau(43) International Publication Date
20 November 2003 (20.11.2003)

PCT

(10) International Publication Number
WO 03/095060 A1(51) International Patent Classification⁷: B01D 19/02, B01J 19/24, F28F 19/06

(74) Agents: DE GREGORI, Antonella et al.; Ing. Barzano' & Zanardo Milano S.p.A, Via Borgonuovo, 10, I- 20121 Milan, IT (IT).

(21) International Application Number: PCT/EP03/04949

(81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(22) International Filing Date: 9 May 2003 (09.05.2003)

(84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:


MI02A001009 13 May 2002 (13.05.2002) IT

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: TUBE BUNDLE APPARATUS FOR PROCESSING CORROSIVE FLUIDS



WO 03/095060 A1

(57) Abstract: Tube bundle apparatus for thermal exchange operations at high pressures and temperatures, under conditions of high aggressiveness of the process fluids, wherein the tube bundle comprises a series of tubes (4) whose internal wall is essentially constituted by a material selected from titanium, zirconium or an alloy of one of these, resistant to the aggression of said fluids, in which at least one of the access chambers to the tube bundle is DELIMITED by a wall comprising at least the following three metallic layers in succession: a) an external layer (21) suitable for tolerating the pressure load, subject to corrosion by contact with said highly aggressive process fluid; b) an intermediate layer (22) made of stainless steel; (c) an anticorrosive lining (23) in contact with said highly corrosive fluid, consisting of a material selected from titanium, zirconium or an alloy of one of these. Said apparatus is particularly used as ex- changer/reactor, for example as a stripper, in the high pressure cycle of synthesis processes of urea.